

**RELIABILITY MONITOR REPORT
FOR**

TQFP Package

Dallas Semiconductor

**4401 South Beltwood Parkway
Dallas, TX 75244-3292**

**This Report was prepared by
Dallas Semiconductor Reliability Engineering**

Summary:

The data in the tables that follow was generated as the result of an on-going Package Reliability Monitor. The assemblies covered by this package monitor are:

ASSY SITE	PINS	PACKAGE		
ATK (Amkor, K)	144	TQFP	ATK (Amkor, K)	32 TQFP
ATK (Amkor, K)	44	TQFP	ATK (Amkor, K)	48 TQFP
ATK (Amkor, K)	52	TQFP	ATK (Amkor, K)	64 TQFP
ATK (Amkor, K)	144	TQFP (Pb-Free)	ATK (Amkor, K)	32 TQFP (Pb-Free)
ATK (Amkor, K)	44	TQFP (Pb-Free)	ATK (Amkor, K)	48 TQFP (Pb-Free)
ATK (Amkor, K)	144	TQFP Exposed Pad	ATP (Amkor, PI)	32 TQFP
ATP (Amkor, PI)	44	TQFP	ATP (Amkor, PI)	48 TQFP
ATP (Amkor, PI)	52	TQFP	OSET	32 TQFP
OSET	48	TQFP	SCC (Stats Chippac	44 TQFP
SCC (Stats Chippac	44	TQFP (Pb-Free)	SCS (Stats Chippac S	44 TQFP
SCS (Stats Chippac S	48	TQFP		

The calculated failure rate for this assembly is:

FAILURE RATE: MTTF (YRS): 18096 FITS: 6.3

The parameters used to calculate this failure rate are as follows:

Cf: 60% Ea: 0.7 Tu: 25 °C

The reliability data follows. At the start of this data is a description of the assembly vehicle used to generate this reliability data. The next section is the detailed reliability data for each stress. The reliability data section includes the latest data available. This report covers data between 1/1/2006 and 12/31/2006.

Assembly Information:

Package Type: TQFP (Pb-Free) 10x10x1.0
 Flammability: UL 94-V0
 Moisture Sensitivity (JEDEC J-STD20A) Level 3
 Date Code Range: 0551 to 0643

MOISTURE SENSITIVITY LEVEL 3

DESCRIPTION	DATE CODE	TEST VEHICLE	CONDITION	READPOINT	QUANTITY	FAILS	FA NO
ULTRASOUND	0551	DS80C320	J-STD-020		8	0	
STORAGE LIFE			125C	24 HRS	8		
MOISTURE SOAK			30C/60% R.H.	192 HRS	8		
CONVECTION REFLOW			260C +/-5C	3 PASS	8	0	
EXTERNAL VISUAL			J-STD-020, 6.1a		8	0	
PRECONDITION U/S			J-STD-020		8	0	
Total:						0	

OPERATING LIFE

DESCRIPTION	DATE CODE	TEST VEHICLE	CONDITION	READPOINT	QUANTITY	FAILS	FA NO
HIGH TEMP OP LIFE	0551	DS80C320	125C, 5.5 VOLTS	1000 HRS	77	0	
Total:						0	

PACKAGE TESTS

DESCRIPTION	DATE CODE	TEST VEHICLE	CONDITION	READPOINT	QUANTITY	FAILS	FA NO
-------------	-----------	--------------	-----------	-----------	----------	-------	-------

SOLDERABILITY (Sn/Pb)	0551	DS80C320	JESD22-B102, COND C	3	0
SOLDERABILITY (Pb-Free)			JESD22-B102, COND C	3	0
X-RAY	0551	DS80C320	MIL-STD-883-2012 : TOP & SIDE VIEW	6	0
PHYSICAL DIMENSIONS			JESD22-B100	6	0
MARK PERMANENCY			JESD22-B107	6	0
LEAD INTEGRITY			JESD22-B105, COND B	6	0
EDX			25 C	6	0
SOLDERABILITY (Sn/Pb)	0631	DS80C320	JESD22-B102, COND C	15	0
SOLDERABILITY (Sn/Pb)	0643	DS80C320	JESD22-B102, COND C	20	0
Total:				0	0

PRECONDITIONING LEVEL 3

DESCRIPTION	DATE CODE	TEST VEHICLE	CONDITION	READPOINT	QUANTITY	FAILS	FA NO
STORAGE LIFE	0551	DS80C320	125C	24 HRS	385		
MOISTURE SOAK			30C/60% R.H.	192 HRS	385		
CONVECTION REFLOW			260C +/-5C	3 PASS	385	0	
Total:						0	0

STORAGE LIFE

DESCRIPTION	DATE CODE	TEST VEHICLE	CONDITION	READPOINT	QUANTITY	FAILS	FA NO
STORAGE LIFE	0551	DS80C320	150C	1000 HRS	77	0	
Total:						0	0

TEMPERATURE CYCLE

DESCRIPTION	DATE CODE	TEST VEHICLE	CONDITION	READPOINT	QUANTITY	FAILS	FA NO
TEMP CYCLE	0551	DS80C320	-55C TO 125C	1000 CYS	77	0	
Total:						0	0

TEMPERATURE HUMIDITY BIAS

DESCRIPTION	DATE CODE	TEST VEHICLE	CONDITION	READPOINT	QUANTITY	FAILS	FA NO
HAST	0551	DS80C320	130C, 85%R.H.,5.5V	96 HRS	44	0	
Total:						0	0

UNBIASED MOISTURE RESISTANCE

DESCRIPTION	DATE CODE	TEST VEHICLE	CONDITION	READPOINT	QUANTITY	FAILS	FA NO
HAST, NO BIAS	0551	DS80C320	130C, 85% R.H.	200 HRS	77	0	
Total:						0	0

Assembly Information:

Package Type: TQFP (Pb-Free) 7x7x1
 Flammability: UL 94-V0
 Moisture Sensitivity (JEDEC J-STD20A) Level 3
 Date Code Range: 0604 to 0604

OPERATING LIFE

DESCRIPTION	DATE CODE	TEST VEHICLE	CONDITION	READPOINT	QUANTITY	FAILS	FA NO
HIGH TEMP OP LIFE	0604	DS3988	125C, 5.5 VOLTS	1000 HRS	77	0	

Total: 0

TEMPERATURE CYCLE

DESCRIPTION	DATE CODE	TEST VEHICLE	CONDITION	READPOINT	QUANTITY	FAILS	FA NO
TEMP CYCLE	0604	DS3988	-55C TO 125C	1000 CYS	77	0	
Total:						0	

TEMPERATURE HUMIDITY BIAS

DESCRIPTION	DATE CODE	TEST VEHICLE	CONDITION	READPOINT	QUANTITY	FAILS	FA NO
HAST	0604	DS3988	130C, 85%R.H.,5.5V	96 HRS	72	0	
Total:						0	

UNBIASED MOISTURE RESISTANCE

DESCRIPTION	DATE CODE	TEST VEHICLE	CONDITION	READPOINT	QUANTITY	FAILS	FA NO
HAST, NO BIAS	0604	DS3988	130C, 85% R.H.	200 HRS	77	0	
Total:						0	

FAILURE RATE: MTTF (YRS): 18096 FITS: 6.3