



6/7/2007

**PRODUCT RELIABILITY REPORT
FOR**

DS26522, Rev A1

Dallas Semiconductor

**4401 South Beltwood Parkway
Dallas, TX 75244-3292**

Prepared by:

**Ken Wendel
Reliability Engineering Manager
Dallas Semiconductor
4401 South Beltwood Pkwy.
Dallas, TX 75244-3292
Email : ken.wendel@dalsemi.com
ph: 972-371-3726
fax: 972-371-6016
mbl: 214-435-6610**

Conclusion:

The following qualification successfully meets the quality and reliability standards required of all Dallas Semiconductor products:

DS26522, Rev A1

In addition, Dallas Semiconductor's continuous reliability monitor program ensures that all outgoing product will continue to meet Maxim's quality and reliability standards. The current status of the reliability monitor program can be viewed at <http://www.maxim-ic.com/TechSupport/dsreliability.html>.

Device Description:

A description of this device can be found in the product data sheet. You can find the product data sheet at http://dbserv.maxim-ic.com/l_datasheet3.cfm.

Reliability Derating:

The Arrhenius model will be used to determine the acceleration factor for failure mechanisms that are temperature accelerated.

$$AfT = \exp((Ea/k) * (1/Tu - 1/Ts)) = tu/ts$$

AfT = Acceleration factor due to Temperature
tu = Time at use temperature (e.g. 55°C)
ts = Time at stress temperature (e.g. 125°C)
k = Boltzmann's Constant (8.617 x 10⁻⁵ eV/°K)
Tu = Temperature at Use (°K)
Ts = Temperature at Stress (°K)
Ea = Activation Energy (e.g. 0.7 ev)

The activation energy of the failure mechanism is derived from either internal studies or industry accepted standards, or activation energy of 0.7ev will be used whenever actual failure mechanisms or their activation energies are unknown. All deratings will be done from the stress ambient temperature to the use ambient temperature.

An exponential model will be used to determine the acceleration factor for failure mechanisms, which are voltage accelerated.

$$AfV = \exp(B * (Vs - Vu))$$

AfV = Acceleration factor due to Voltage
Vs = Stress Voltage (e.g. 7.0 volts)
Vu = Maximum Operating Voltage (e.g. 5.5 volts)
B = Constant related to failure mechanism type (e.g. 1.0, 2.4, 2.7, etc.)

The Constant, B, related to the failure mechanism is derived from either internal studies or industry accepted standards, or a B of 1.0 will be used whenever actual failure mechanisms or their B are unknown. All deratings will be done from the stress voltage to the maximum operating voltage. Failure rate data from the operating life test is reported using a Chi-Squared statistical model at the 60% or 90% confidence level (Cf).

The failure rate, Fr, is related to the acceleration during life test by:

$$Fr = X / (ts * AfV * AfT * N * 2)$$

X = Chi-Sq statistical upper limit
N = Life test sample size

Failure Rates are reported in FITs (Failures in Time) or MTTF (Mean Time To Failure). The FIT rate is related to MTTF by:

$$MTTF = 1/Fr$$

NOTE: MTTF is frequently used interchangeably with MTBF.

The calculated failure rate for this device/process is:

FAILURE RATE:	MTTF (YRS):	182793	FITS:	0.6
	DEVICE HOURS:	1555640	FAILS:	0

Only data from Operating Life or similar stresses are used for this calculation.

The parameters used to calculate this failure rate are as follows:

Cf: 60% **Ea: 0.7** **B: 0** **Tu: 25 °C** **Vu: 5.5 Volts**

The reliability data follows. At the start of this data is the device information. The next section is the detailed reliability data for each stress. The reliability data section includes the latest data available and may contain some generic data. "*" after DATE CODE denotes specific product data and SEQ No. to identify specific line items in the report for comments when required.

Device Information:

Process: 2P, 4M,0.35um,Sil.P1,P2Cap,Ti/TiN M1-M4,BPSG,Masked N+ESD,
 Passivation: Passivation w/Nov TEOS Oxide-Nitride
 Die Size: 155 x 270
 Number of Transistors: 1307792
 Interconnect: Aluminum / 0.5% Copper
 Gate Oxide Thickness: 75 Å

ELECTRICAL CHARACTERIZATION

DESCRIPTION	DATE CODE/SEQ	CONDITION	READPOINT	QTY	FAILS	FA#
ESD SENSITIVITY	0542 * 1	EOS/ESD S5.1 HBM 500 VOLTS	1 PUL'S	3	0	
ESD SENSITIVITY	0542 * 5	EOS/ESD S5.1 HBM 8000 VOLTS	1 PUL'S	3	0	
ESD SENSITIVITY	0542 * 2	EOS/ESD S5.1 HBM 1000 VOLTS	1 PUL'S	3	0	
ESD SENSITIVITY	0542 * 3	EOS/ESD S5.1 HBM 2000 VOLTS	1 PUL'S	3	0	
ESD SENSITIVITY	0542 * 4	EOS/ESD S5.1 HBM 4000 VOLTS	1 PUL'S	3	0	
ESD SENSITIVITY	0542 * 5	EOS/ESD S5.1 HBM 8000 VOLTS	1 PUL'S	3	0	
LATCH-UP	0542 * 6	JESD78, I-TEST 85C		6	0	
LATCH-UP	0542 * 7	JESD78, V-SUPPLY TEST 125C		6	0	
Total:					0	

OPERATING LIFE

DESCRIPTION	DATE CODE/SEQ	CONDITION	READPOINT	QTY	FAILS	FA#
HIGH TEMP OP LIFE	0403	125C, 3.5 VOLTS	1000 HRS	45	0	
HIGH TEMP OP LIFE	0417	125C, 3.5 VOLTS	1000 HRS	45	0	
HIGH TEMP OP LIFE	0418	125C, 3.5 VOLTS	1000 HRS	45	0	
HIGH TEMP OP LIFE	0425	125C, 3.5 VOLTS	1000 HRS	44	0	

HIGH TEMP OP LIFE	0436		125C, 3.5 VOLTS	1000 HRS	45	0
HIGH TEMP OP LIFE	0440		125C, 3.5 VOLTS	1000 HRS	45	0
HIGH TEMP OP LIFE	0442		125C, 3.5 VOLTS	1000 HRS	45	0
HIGH TEMP OP LIFE	0447		125C, 3.5 VOLTS	1000 HRS	45	0
HIGH TEMP OP LIFE	0448		125C, 3.5 VOLTS	1000 HRS	45	0
HIGH TEMP OP LIFE	0501		125C, 3.5 VOLTS	1000 HRS	45	0
HIGH TEMP OP LIFE	0518		125C, 3.5 VOLTS	1000 HRS	45	0
HIGH TEMP OP LIFE	0520		125C, 3.5 VOLTS	1000 HRS	44	0
HIGH TEMP OP LIFE	0525		125C, 3.5 VOLTS	1000 HRS	77	0
HIGH TEMP OP LIFE	0527		125C, 3.5 VOLTS	1000 HRS	45	0
HIGH TEMP OP LIFE	0536		125C, 3.5V (PSA) & 2.0V (PSB)	1000 HRS	45	0
HIGH TEMP OP LIFE	0537		125C, 3.5 VOLTS	1000 HRS	45	0
HIGH TEMP OP LIFE	0542	* 1	125C, 3.5 VOLTS	192 HRS	45	0
HIGH TEMP OP LIFE	0548		125C, 3.5 VOLTS	1000 HRS	45	0
HIGH TEMP OP LIFE	0604	* 6	125C, 3.5 VOLTS	1000 HRS	45	0
HIGH TEMP OP LIFE	0606		125C, 3.5 VOLTS	1000 HRS	45	0
HIGH TEMP OP LIFE	0614		125C, 3.5 VOLTS	1000 HRS	45	0
HIGH TEMP OP LIFE	0616		125C, 3.5 VOLTS	1000 HRS	45	0
HIGH TEMP OP LIFE	0616		125C, 3.5 VOLTS	1000 HRS	45	0
HIGH TEMP OP LIFE	0616		125C, 3.5 VOLTS	1000 HRS	45	0
HIGH TEMP OP LIFE	0617		125C, 3.6 VOLTS	1000 HRS	45	0
HIGH TEMP OP LIFE	0617		125C, 3.6 VOLTS	1000 HRS	45	0
HIGH TEMP OP LIFE	0617		125C, 3.6 VOLTS	1000 HRS	45	0
HIGH TEMP OP LIFE	0618		125C, 3.5 VOLTS	1000 HRS	77	0
HIGH TEMP OP LIFE	0620		125C, 3.5 VOLTS	1000 HRS	45	0
HIGH TEMP OP LIFE	0632		125C, 3.5 VOLTS	1000 HRS	45	0
HIGH TEMP OP LIFE	0632		125C, 3.5 VOLTS	1000 HRS	45	0
HIGH TEMP OP LIFE	0641		125C, 3.5 VOLTS	1000 HRS	45	0
HIGH TEMP OP LIFE	0650	* 5	125C, 3.5 VOLTS	1000 HRS	45	0
HIGH TEMP OP LIFE	0650	* 5	125C, 3.5 VOLTS	1000 HRS	45	0

Total: 0

FAILURE RATE: MTTF (YRS): 182793 FITS: 0.6
DEVICE HOURS: 1555640 FAILS: 0